

## **SANI-ARMOR HDPE**

## **Physical Properties**

iPoly's Sani-Armor high density polyethylene (HDPE) is used in a variety of applications and industries where excellent impact resistance, high tensile strength, low moisture absorption and chemical and corrosion-resistance properties are required. The combination of excellent molecular structure and superior environmental stress crack resistance makes our HDPE ideal for fabrications and weldments. This resin meets the Food and Drug Administration requirement for direct food contact; please refer to FDA data sheet for certified information on food

## **TECHNICAL INFORMATION**

Property	Method	Unit	Nominal Value*
Density	ASTM D-792	g/cm3	0.954
Tensile strength at yield	<b>ASTM D-638</b>	psi	4000
Tensile modulus	<b>ASTM D-638</b>	psi	<mark>n/a</mark>
Elongation at yield	ASTM D-638	%	18
Elongation at break	ASTM D-638	%	700
Tensile impact	DIN 53448	ft-lbs/in2	<del>550</del>
Flexural modulus	<b>ASTM D-790</b>	psi	165,000
Flexural strength	<b>ASTM D-790</b>	psi	3,800
Izod impact	ASTM D-4020	ft-lbs/in2	17
IZOD impact notched	ASTM D-2240	ft-lbs/in2	3.5
Compressive modulus	ASTM D-695	psi	n/a
Compressive deformation	ASTM D-621	% at 1000 psi	n/a
Melting point	ASTM D-3417	°F	290
Hardness	ASTM D-2240	Shore D	65
Coefficient of linear thermal expansion	<b>ASTM D-696</b>	in/in/°F	$6.7 \times 10^{-5}$
Heat deflection temperature, 66 psi	ASTM D-648	°F	165
Max. operating temp.		°F	170
Volume Resistivity	ASTM D-257	Ohm-cm	>10 <sup>15</sup>
Surface Resistivity	ASTM D-257	Ohm	>10 <sup>15</sup>
Water absorption 24hrs.	ASTM D-570	%	0.0001

**Disclaimer**: All technical information and recommendations contained herein though believed to be true in nature are meant as general guidelines only. As such iPoly makes no express or implied warranties regarding end uses of these materials. Buyers are responsible for determining the specific material requirements for a given application. Any damages, direct or consequential, resulting from the use of these materials are strictly the responsibility of the buyer. iPoly will not be responsible or held liable for the improper use of our materials in regards to patent infringements, nor should any of our literature be construed as an offer of indemnity for patent infringement. @2010 iPoly, Thorold, ON.